

# TECHNICAL

## HARDNESS CONVERSION TABLE

Rockwell Hardness			Brinell	Tensile Strength
C	B	A	Hardness	(Lbs./Sq.In.)
70		86.5	780	
69		86.0	762	
68		85.5	745	
67		85.0	728	
66		84.5	712	
65		84.0	697	
64		83.5	682	
63		83.0	668	
62		82.5	653	
61		82.0	640	
60		81.0	627	314,000
59		80.5	614	307,000
58		80.0	601	299,000
57		79.5	578	291,000
56		79.0	567	284,000
55		78.5	555	277,000
54		78.0	545	270,000
53		77.5	534	263,000
52		77.0	514	256,000
51		76.5	505	250,000
50		76.0	495	243,000
49		75.5	477	236,000
48		75.0	469	230,000
47		74.0	461	223,000
46	115	73.5	444	217,000
45	115	73.0	429	211,000
44	114	72.5	415	205,000
43	114	72.0	408	200,000
42	113	71.5	401	195,000
41	112	71.0	388	188,000
40	112	70.5	375	182,000
39	111	70.0	369	176,000

Rockwell Hardness			Brinell	Tensile Strength
C	B	A	Hardness	(Lbs./Sq.In.)
38	110	69.5	363	171,000
37	110	69.0	352	167,000
36	109	68.5	341	162,000
35	109	68.0	331	158,000
34	108	67.5	321	153,000
33	108	67.0	311	148,000
32	107	66.5	302	144,000
31	106	66.0	293	140,000
30	105	65.5	285	136,000
29	104	65.0	277	133,000
28	104	64.5	269	131,000
27	103	64.0	265	130,000
26	103	63.5	262	128,000
25	102	63.0	255	125,000
24	102	62.5	248	122,000
23	101	62.0	241	119,000
22	100	61.5	235	116,000
21	99	61.0	229	113,000
20	98	60.0	223	110,000
19	97	59.5	220	108,000
18	97	59.0	217	107,000
17	96	58.0	212	104,000
16	96	57.5	207	101,000
15	95	57.0	202	99,000
14	94	56.5	200	98,000
13	93	56.0	197	97,000
12	92	55.5	192	95,000
11	92	55.0	189	94,000
10	91	54.0	187	93,000
9	90	53.5	183	91,000
8	89	53.0	179	89,000
7	88	52.5	174	87,000

